

Niax™ catalyst A-300

Niax* catalyst A-300

Description

Niax catalyst A-300 can help in the production of your molded polyurethane foams. This liquid, water-soluble tertiary amine composition promotes the gelation reaction during the production process. But all resemblance to other catalysts ends with the Niax catalyst A-300's unique delayed-action enhancement. Niax catalyst A-300 and Niax catalyst A-400 belong to a new class of delayed-action catalysts that jump-start the efficiency of your operation by delaying the reaction while producing substantially more open foam.

Niax catalyst A-300 is the better-flow choice for automotive and upholstered furniture applications. This performance-oriented catalyst readily adapts to your operation: add the Niax catalyst A-300 as a separate stream or blend it with water or polyol for metering to the mixing head of the machine.

Key Features and Benefits

Niax catalyst A-300 delivers added value with performance features that include:

- Improved flow in the mold for
 - Easier production of complex parts
 - Density reduction of 1-5%
- Considerable reduction in force-to-crush, signifying enhanced production of open foam when compared with competitive delayed-action catalysts
- Much lower amine fugitivity
- Far less corrosive to mild steel

Typical Physical Properties

Specific Gravity at 25°C	1.108
Viscosity at 25°C, cP	9.6
Solubility in Water at 20°C	Complete

(1) ASTM Test Method D93

Potential Applications

Niax catalyst A-300 is a targeted catalyst for use in the production of a wide variety of automotive seating and worldwide contact upholstered furniture. Excellent flow in the mold performance and other unique features also make the Niax catalyst A-300 very suitable for a wide variety of automotive interior parts applications.

Please note that:

- The activity of Niax catalyst A-300 is similar to that of Niax catalyst A-33
- The Niax catalyst A-300's delayed action feature is particularly useful with MDI and TDI/MDI blends
- In a typical molded-foam application, the delayed gel provided by Niax catalyst A-300 should be used in combination with a blowing catalyst such as Niax catalyst A-1.

Processing Recommendations

Table 1 shows the performance of Niax catalyst A-300 in a typical MDI formulation and clearly illustrates the Niax catalyst A-300 details that make the difference:

- Niax catalyst A-300 yields more open foam than competitive delayed-action gel catalysts
- The flow is significantly better than that of competitive products
- Of considerable importance is the 56% reduction in the force-to-crush at low index while preserving cure (as shown by the hot ILD values)
- In the maze mold, Niax catalyst A-300's improved flow benefits allow a reduction in the minimum weight to fill the mold, resulting in a density reduction across the index range

Table: 1 Performance of Niax catalyst A-300 in Molded Foam

MDI FORMULATION, NCO = 29.4		php	
Components		A	B
Polyol OH# 28		100.0	100.0
Water		3.8	3.8
Niax catalyst A-1		0.2	0.2
Niax catalyst A-300		0.8	-
Competitive Catalyst		—	0.8
Diisopropanolamine		2.0	2.0
Niax Silicone Surfactant Y-10366 (RS-171)		1.0	1.0
FOAM PROPERTIES ^(1, 2)			
Square Mold			
MDI Index	80	80	
Foam Weight, g	402	400	
F.T.C., N	376	850	
Hot ILD, N	202	192	
Exit Time, Sec	47	48	
Maze Mold			
MDI Index	80	80	
Minimum Weight to fill, g	410	419	
Flowability	Good	Subsurface Collapse	
Shrinkage	Slight	Severe	
Maze Mold			
MDI Index	100	100	
Minimum Weight to Fill, g	372	395	
Exit Time, sec	49	46	

(1) F.T.C. is the force to indent at 50% an uncrushed cushion at 1 min. after demold.

(2) Hot ILD is the force to indent at 50% a crushed cushion at 3 min. after demold.

Patent Status

Standard copy to come

Product Safety, Handling and Storage

Standard copy to come

Limitations

Standard copy to come

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas	Latin America	EMEAI- Europe, Middle East, Africa & India	ASIA PACIFIC
+1 800 295 2392 Toll free* +704 805 6946 Direct Number	Brazil +55 11 4534 9650 Direct Number	Europe +390510924300 Direct number	China 800 820 0202 Toll free +86 21 3860 4892 Direct number
All American countries	Mexico +52 55 2169 7670 Direct Number	India, Middle East & Africa + 91 44 71212207 Direct number *All Middle Eastern countries, Africa, India,	Japan +81 3 5544 3111 Direct number Korea +82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR

GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*Niax™ is a trademark of Momentive Performance Materials Inc.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.