

CoatOSil* T-Cure Silane Oligomer



MARKETING BULLETIN

SILANES - COATINGS ADDITIVES

CoatOSil T-Cure silane oligomer may be useful in the development of coating formulations where reactivity with a mercapto silane is desired. This patented oligomer is low in odor compared to standard mercapto silanes and can display a trio of reactive chemistries. In addition to thiol groups, silanol and diols are generated upon the hydrolysis of the silane.


Key Features and Typical Benefits

- Less than 1%wt releasable ethanol
- Low odor
- Low viscosity
- Behaves as reactive diluent within a coating formulation
- Can be used in virtually all coating chemistries where mercapto groups can react, e.g.;
 - Isocyanates
 - Epoxies
 - Acrylates

Potential Applications

- Coatings for industrial maintenance applications including storage tanks, bridges and exterior steel structures
- Coatings requiring curing at elevated temperatures (heat cured formulations), such as coatings for automotive, appliance or coil applications
- Epoxy primers for metals and flooring
- Room temperature cure coatings for applications such as aerospace and automotive re-finishing

Chemical Structure



Typical Physical Properties

Property	Value
Density (gm/cm ³) at 25 °C	1.105
Viscosity at 25 °C (cPs)	~400
Refractive Index at 25 °C	~1.4745
Surface Tension at 25 °C (dyne/cm)	~34.65

Typical properties are average data and are not to be used as or to develop specifications.

General Considerations for Use

Typical dosage levels in coating formulations where mercaptos can react are between 1%wt to 10%wt in existing formulations on a total resin solids basis. Higher levels of CoatOSil T-Cure silane oligomer may also be incorporated into formulations as necessary.

Example 1: Use in Isocyanate and Acrylate Based Formulations

When formulated into an isocyanate based coating formulation, CoatOSil T-Cure silane can improve a number of physical properties. To explore these effects, CoatOSil T-Cure silane was tested at addition levels of 3% and 10% by weight in Part A of the Clearcoat formulation (Ex#1 and Ex#2). In order to clarify the role of the silane portion of the molecule, the representative amount of glycol that would be contributed by the 3% and 10% additions of silane was tested in stoichiometrically adjusted formulations (Ex#3 and Ex#4 respectively) similar to the control.



In polyurethane systems CoatOSil T-Cure has an approximate equivalent weight of 60 grams/eq.

Sample Clearcoat Formulations


%wt CoatOSil T-Cure Silane Oligomer on Part A		0.0%	3%	10%	0.0%	0.0%
%wt Glycol ⁽¹⁾		0.0%	0.0%	0.0%	2.1%	7.2%
Part A	Control	Ex#1	Ex#2	Ex#3	Ex#4	
Material	T.S.	T.S.	T.S.	T.S.	T.S.	
Acrylamac 232-1375 [†] Resin	15.77	14.75	12.63	14.87	12.99	
CoatOSil T-Cure Silane Oligomer	0.00	0.33	1.02	0.00	0.00	
Glycol	0.00	0.00	0.00	0.24	0.73	
Gel Paste Intermediate	1.62	1.57	1.45	1.56	1.44	
Acrylamac 232-1375 [†] Resin	0.49	0.47	0.44	0.47	0.43	
Fumed Silica	0.07	0.07	0.06	0.07	0.06	
N-Butyl Acetate	1.06	1.03	0.95	1.03	0.95	
UVA	0.40	0.39	0.36	0.39	0.36	
HAL	0.11	0.11	0.10	0.11	0.10	
CoatOSil 2816 Additive	0.03	0.03	0.02	0.03	0.02	
Catalyst Intermediate	0.57	0.55	0.51	0.55	0.51	
DBTDL	0.03	0.03	0.03	0.03	0.03	
N-Butyl Acetate	0.54	0.52	0.48	0.52	0.48	
N-Butyl Acetate	4.55	4.39	4.07	4.39	4.05	
Methyl Ethyl Ketone	2.84	2.75	2.54	2.74	2.53	
	25.90	24.86	22.70	24.87	22.74	
Part B	Control	Ex#1	Ex#2	Ex#3	Ex#4	
Isocyanate Solution	9.12	10.16	12.32	10.14	12.27	
HDI Trimer	6.38	7.11	8.62	7.10	8.59	
N-Butyl Acetate	2.74	3.05	3.70	3.04	3.68	
Total	35.02	35.02	35.01	35.02	35.01	

Product formulations are included as illustrative examples only. Momentive makes no representation or warranty of any kind with regard to any such formulations, including, without limitation, concerning the efficacy or safety of any product manufactured using such formulations.



Neutral Salt Spray Results



Note: Test data. Actual results may vary.



	Control	+3% CoatOSil T-Cure Silane	+10% CoatOSil T-Cure Silane	+2.3% Glycol	+7.2% Glycol
■ Set-to-Touch	11	22	26	15	15
■ Tack-Free	22	67	78	26	30
■ Dry-Hard	45	94	97	52	49



Exhibited Benefits of CoatOSil T-Cure Silane Oligomer in NCO Coating Formulations:

- Higher initial surface hardness of coatings
- QUV-B gloss and color change was equal to the control. QUV-A results were similar when tested.
- NSST corrosion resistance appears to have been better than the control
- Greater open time during cure, which may potentially lead to a longer pot-life after mixing
- An excellent candidate to consider for both castable and RIM urethane and urea applications


Note: Test data. Actual results may vary.

Example 2: Use in Epoxy Based Formulations

CoatOSil T-Cure silane oligomer was tested in epoxy based coating formulations to determine its performance in primers. In epoxy curing applications, CoatOSil T-Cure silane has an approximate equivalent weight of 400 ± 50 gramseq.

Control		Control + 1%wt CoatOSil T-Cure Silane		White Topcoat	
Material	T.S.	Material	T.S.	PART A	CONTROL
EPOXY GRIND PASTE	154.38	EPOXY GRIND PASTE	153.47	Material	T.S.
Epon 828 [†] Epoxy	27.59	Epon 828 [†] Epoxy	27.42	Acrylamac 232-1375 ^{††} Resin	17.77
Epon 1001F [†] Epoxy	14.39	Epon 1001F [†] Epoxy	14.31	WHITE GRIND PASTE	26.34
TiO ₂ Pigment	29.99	TiO ₂ Pigment	29.81	Acrylamac 232-1375 [†] Resin	5.27
Barium Sulfate	7.50	Barium Sulfate	7.45	Fumed Silica	0.12
Carbon Black	1.50	Carbon Black	1.49	Titanium Dioxide	16.01
N-Butyl Acetate	35.64	N-Butyl Acetate	35.43	N-Butyl Acetate	4.95
Talc Powder	7.50	Talc Powder	7.45	UVA	0.57
Bentone	0.30	Bentone	0.30	HAL	0.16
Epon 828 [†] Epoxy	29.99	Epon 828 [†] Epoxy	29.81	CoatOSil 2816 Additive	0.02
AMINE BLEND	30.17	AMINE BLEND	30.57	CATALYST INTERMEDIATE	0.81
EpiKure 3115E-73 [†] Amine	7.68	EpiKure 3115E-73 [†] Amine	7.60	DBTDL	0.04
EpiKure 3200 [†] Amine	2.86	EpiKure 3200 [†] Amine	2.83	N-Butyl Acetate	0.77
EpiKure 3251 [†] Amine	19.62	CoatOSil T-Cure Silane Oligomer	0.72	N-Butyl Acetate	1.41
		EpiKure 3251 [†] Amine	19.42		47.08
TOTAL	184.55	TOTAL	184.49	NCO/OH = 1.05	
				PART B	
				ISOCYANATE SOLUTION	12.92
				HDI Trimer	9.04
				N-Butyl Acetate	3.88
					60.00

Product formulations are included as illustrative examples only. Momentive makes no representation or warranty of any kind with regard to any such formulations, including, without limitation, concerning the efficacy or safety of any product manufactured using such formulations.

Primers Coated with White Topcoat

3M 898 Mesh Tape Used

Exhibited Benefits of CoatOSil T-Cure Silane Oligomer in Epoxy Coating Formulations:

- Improved adhesion to metal substrates at low loading concentrations
- No adverse effect on epoxy cure time

Additional Considerations:

Hydrolysis of CoatOSil T-Cure silane oligomer may occur with water and alcohols resulting in a stronger mercapto smell.

CoatOSil T-Cure silane oligomer is not recommended for use with amines or epoxies containing alcohols.

Note: Test data. Actual results may vary.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative.

For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Customer Service Centers

WorldwideEmail: commercial.services@momentive.com**Americas**+1 800 295 2392
+1 614 986 2495**Europe, Middle East,
Africa and India**00800 4321 1000
+40 213 044229**Asia Pacific****China**
800 820 0202
+86 21 3860 4892**All Other Countries**
+60 3 9206 1543**Japan**
0120 975 400
+81 276 20 6182

Disclaimer

FORMULATIONS ARE ILLUSTRATIVE EXAMPLES AND DO NOT REPRESENT COMMERCIALIZED PRODUCTS. They have not been subjected to extensive testing and Momentive makes no representation or warranty of any kind with regard to any such formulations, including, without limitation, concerning the performance, efficacy or safety of any product manufactured using such formulations. EACH USER BEARS FULL RESPONSIBILITY FOR (1) MAKING ITS OWN DETERMINATION AS TO THE SUITABILITY AND LEGAL COMPLIANCE OF ANY FORMULATION, MATERIALS, RECOMMENDATIONS, OR ADVICE FOR ITS OWN PARTICULAR USE, (2) IDENTIFYING AND PERFORMING ALL TESTS AND ANALYSES NECESSARY TO ASSURE THAT ITS FINISHED PRODUCTS BASED UPON EXAMPLE FORMULATIONS AND/OR INCORPORATING MENTIONED PRODUCTS, MATERIALS, OR SERVICES WILL BE SAFE AND SUITABLE FOR USE UNDER END-USE CONDITIONS, AND (3) OBTAINING ANY NECESSARY GOVERNMENT OR REGULATORY CLEARANCE, LICENSE OR REGISTRATION.

Any reference to a third party's materials is not an endorsement of those materials or an endorsement by the third party of Momentive materials. Momentive has not undertaken a comprehensive patent or other intellectual property search on the formulations. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

BEFORE HANDLING ANY PRODUCTS MENTIONED, REVIEW THE LATEST SAFETY DATA SHEET (SDS) AND LABEL FOR PRODUCT SAFETY INFORMATION, SAFE HANDLING INSTRUCTIONS, PERSONAL PROTECTIVE EQUIPMENT IF NECESSARY, EMERGENCY SERVICE CONTACT INFORMATION, AND ANY SPECIAL STORAGE CONDITIONS REQUIRED FOR SAFETY. MOMENTIVE MAINTAINS AN AROUND-THE-CLOCK EMERGENCY SERVICE FOR ITS PRODUCTS. SDS FOR MOMENTIVE PRODUCTS ARE AVAILABLE AT WWW.MOMENTIVE.COM OR, UPON REQUEST, FROM ANY MOMENTIVE REPRESENTATIVE. USE OF OTHER MATERIALS IN CONJUNCTION WITH MOMENTIVE PRODUCTS MAY REQUIRE ADDITIONAL PRECAUTIONS. PLEASE REVIEW AND FOLLOW THE SAFETY INFORMATION PROVIDED BY THE MANUFACTURER OF SUCH OTHER MATERIALS.

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier.