

Silquest* A-Link* 600 Aminosilane



MARKETING BULLETIN

SILANES - ADHESIVES & SEALANTS ADDITIVES

Silquest A-Link 600 silane is a non-yellowing adhesion promoter that can provide sealant, adhesives and coatings with good flexibility and excellent adhesion compared to other functional silanes. Silquest A-Link 600 silane may be considered for use with SPUR+* technology-based, silicone, urethane, epoxy, silylated polyether and polyurethane adhesives, sealants and coatings.

Formulators using Silquest A-Link 600 silane in SPUR+ prepolymer-based systems typically experience higher elongation and lower modulus than conventional aminosilanes provide. Silquest A-Link 600 silane can provide the greatest benefit in systems requiring low color formation and improved flexibility.

Silquest A-Link 600 silane helps formulators develop low yellowing sealant formulations with improved flexibility and high elastic recovery while maintaining the excellent adhesion common to conventional aminosilanes.

Key Features and Typical Benefits

- Low yellowing under UV and thermal exposure
- Helps to optimize sealant modulus and elongation
- Improved joint movement desirable in construction sealants
- Excellent adhesion to a variety of substrates for performance across numerous organic and inorganic surfaces

Potential Applications

Silquest A-Link 600 silane is a good candidate to consider for use in silicone, epoxy, urethane, silylated polyurethane and polyether adhesives, sealants and coatings:

- Moisture curable, specialty construction sealants
- SPUR+ prepolymer hybrid sealants and adhesives
- Polyurethane sealants
- Silicone RTV applications
- Clearcoats and paints for architectural, automotive, industrial and marine coatings


Typical Physical Properties

Property	Value
Actives Content, %wt	100
Specific Gravity at 25 / 25 °C	0.9762
Amine Equivalent Weight (m/kg)	4.5
Flash Point °C (°F)	97 (207)

Typical properties are average data and are not to be used as or to develop specifications.

Color Stability

To determine the color stability performance, Silquest A-Link 600 silane and three other silanes were evaluated after four weeks of QUV B exposure. Results showed that Silquest A-Link 600 silane maintained a color close to that of the water sample. When formulated appropriately, it can offer significantly lower yellowing compared to other aminosilanes.




Note: Test results. Actual results may vary.

Color Stability in SPUR⁺ Prepolymer-based Clear Sealant Formulations

To understand how Silquest A-Link 600 silane would perform in a sealant formulation, it was exposed to QUV A for 7 days. Each of the other three silanes used above were also tested using the same amount in the same formulation. After the test was complete, Silquest A-Link 600 silane proved to be more stable than the conventional amino functional silanes when placed under prolonged UV exposure.

Ingredients	(Wt. %)
SPUR ⁺ 1050MM Prepolymer	51.0
Benzoate Plasticizer	32.9
Antioxidant	1.3
Fumed Silica	11.3
Silquest A-171* Silane	1.7
Aminosilane	1.5
Formrez [†] SUL-4 Catalyst	0.3



Note: Test results. Actual results may vary.

Product formulations are included as illustrative examples only. Momentive makes no representation or warranty of any kind with regard to any such formulations, including, without limitation, concerning the efficacy or safety of any product manufactured using such formulations.

Color Stability in Polyurethane Formulations

Measured by a Minolta Colorimeter, the color stability of Silquest A-Link 600 silane was compared to Silquest A-1120 silane, Silquest A-1110 silane and Silquest A-Link 15 silane. The results showed the color change (Δb) of a traditional moisture-cure aromatic polyurethane sealant formulation to be far less when using Silquest A-Link 600 silane compared to the three other amino functional silanes.

Silanes	Initial			After 5-days at 80 °C			Δb
	L	a	b	L	a	b	
Silquest A-1120	89.83	0.05	6.52	86.96	-1.55	20.83	14.31
Silquest A-1110	91.1	0.16	4.8	91.45	-1.52	14.76	9.96
Silquest A-Link 15	91.58	0.14	4.6	89.71	-0.1	12.07	4.47
Silquest A-Link 600	91.2	0.22	4.52	91.57	-0.25	6.3	1.78
Aromatic polyurethane formulation with 2.5% silane addition level.							

Note: Test results. Actual results may vary.

Performance in 13 % SPUR+* Prepolymer-based Sealant Formulation

Silquest A-Link 600 silane was tested in a low-use level SPUR+ prepolymer-based sealant formulation and then compared to the results of two identical formulations utilizing either an oligomeric aminosilane or Silquest A-1120 silane. Results show that Silquest A-Link 600 silane provided a lower modulus and enhanced flexibility compared to the other silanes. In turn, it can be used to give more flexibility to a sealant or adhesive, while maintaining adhesion over a variety of tested substrates.

Ingredients	(Wt. %)	Silane Additive Used	Silquest A-1120 Silane	Commercial Benchmark: Oligomeric Aminosilane	Silquest A-Link 600 Silane
SPUR+ 1050MM Prepolymer	13.1				
DINP Plasticizer	27.2				
Titanium Dioxide	1.1				
Fumed Silica	2.2				
GCC / PCC Mix (Calcium Carbonate)	54.5				
Silquest A-171* Silane	1.1				
Aminosilane	0.73				
Formrez† SUL-4 Catalyst	0.08				
		Mechanical Properties(a)			
		Tensile Strength (Psi)	140	143	127
		Elongation (%)	185	252	287
		Modulus at 100 % E (Psi)	125	112	83
		Hardness Shore A	33	32	28
		Tear Resistance (lb/in)	29	24	25
		Adhesion – Peel Strength (lb/in / % CF) After 7 Days Water Immersion(b)			
		Glass	18 / 100%	18 / 100%	16 / 100%
		Aluminum	19 / 100%	16 / 100%	19 / 100%
		PVC	18 / 100%	12 / 100%	15 / 100%
		Nylon	18 / 100%	3 / 10%	13 / 100%

Lab test formulation, did not include UV stabilizers. UV stabilizers may be included in actual formulations.

Product formulations are included as illustrative examples only. Momentive makes no representation or warranty of any kind with respect to any such formulations, including, without limitation, concerning the efficacy or safety of any product manufactured using such formulations.

Note: Test results. Actual results may vary.

Performance in 23 % SPUR+ Prepolymer-based Sealant Formulation

Silquest A-Link 600 silane was then tested in a high-use level SPUR+ prepolymer-based sealant formulation and compared to the results of two identical formulations utilizing Silquest A-1120 silane and Silquest A-1110 silane. When using Silquest A-Link 600 silane in a formulation with SPUR+ 1015LM prepolymer, a more flexible and elastic system can be obtained over conventional aminosilane adhesion promoters.

Ingredients	(Wt. %)	Silane Additive Used	Silquest A-1120 Silane	Silquest A-1110 Silane	Silquest A-Link 600 Silane
SPUR+ 1015LM Prepolymer	23.0				
DINP Plasticizer	18.3				
Titanium Dioxide	1.2				
Fumed Silica	1.2				
GCC / PCC Mix (Calcium Carbonate)	55.1				
UV Stabilizer	0.5				
Silquest A-171* Silane	0.3				
Aminosilane	0.57				
Formrez† SUL-4 Catalyst	0.03				
		Mechanical Properties(a)			
		Tensile Strength (Psi)	161	176	182
		Elongation (%)	651	626	1073
		100 % Modulus (Psi)	60	57	39
		Tear Resistance (lb/in)	46	40	45
		Hardness Shore A	20	22	13
		Adhesion – Peel Strength (lb/in / % CF) After 7 Days Water Immersion(b)			
		Glass	21 / 100%	26 / 100%	19 / 100%
		Aluminum	19 / 100%	18 / 100%	16 / 100%
		ABS	22 / 100%	20 / 100%	19 / 100%
		PVC	16 / 100%	17 / 100%	15 / 100%
		Polystyrene	21 / 80%	23 / 100%	18 / 100%
		Nylon	26 / 100%	24 / 10%	16 / 100%

Product formulations are included as illustrative examples only. Momentive makes no representation or warranty of any kind with respect to any such formulations, including, without limitation, concerning the efficacy or safety of any product manufactured using such formulations.

Note: Test results. Actual results may vary.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative.

For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.



www.momentive.com

260 Hudson River Road
Waterford, NY 12188 USA

Customer Service Centers

Email: commercial.services@momentive.com

Americas

+1 800 295 2392
+1 614 986 2495

Europe, Middle East, Africa and India

00800 4321 1000
+40 213 044229

Asia Pacific

China
800 820 0202
+86 21 3860 4892

Japan
0120 975 400
+81 276 20 6182

All Other Countries
+60 3 9206 1543

Disclaimer

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.