

Silopren™ UV LSR 2030 and UV LSR 2060 Liquid Silicone Rubbers

Product Description

Silopren UV LSR 2030 and UV LSR 2060 liquid silicone rubbers belong to a new family of UV curing materials that can offer the benefit of high cure speed at low temperature in injection molding processes.

The processing of Silopren UV LSR 2030 and UV LSR 2060 liquid silicone rubbers is typically distinguished by:

- cure on demand
- very fast curing by UV light at low temperature
- low clamping forces due to low cavity pressure
- transparent mold materials

Key Features and Typical Benefits

Silopren UV LSR 2030 and UV LSR 2060 vulcanizates have comparable properties with conventional LSR materials

- excellent thermal stability
- high stability and flexibility at low temperatures
- good rubber-like properties
- long service life at dynamic stress
- high stability to ozone and ultraviolet light
- excellent dielectric behavior over a wide range of temperatures
- not readily combustible, does not melt or drip

Potential Applications

- Kitchen utensils
- Infant care products
- Lighting
- Displays
- Portable electronic devices
- Advanced aesthetics
- Orthopedics/prosthetics
- Pharmaceutical closures
- Instrument grips
- Valves
- Respiratory/anesthesia
- Medical equipment keypads
- Dental/surgical devices
- Two-component applications

Typical Physical Properties

	UV LSR 2030 UV LSR 2060	UV LSR 2030 UV LSR 2060
Appearance	Colorless, translucent	Colorless, translucent
Viscosity base [Pa*s] at 10 ^{s-1}	450	1000
Viscosity cat [Pa*s] at 10 ^{s-1}	10	10
Properties of the Vulcanizate Mixing ratio of components Base: Catalyst 100:2 Laboratory Vulcanization Conditions: exposure to UV light for 2 min at an intensity of 60 mW/cm ² UV- A†		
Hardness [Shore A]	28	28
Density [g/cm ³]	1,090	1,142
Tensile Strength [MPa]	6,5	12,5
Elongation at Break [%]	700	450
Tear [N/mm]	10	20
Properties of the Vulcanizate With additional post curing 4 h at 200°C		
Hardness [Shore A]	29	59
Density [g/cm ³]	1,091	1,147
Tensile Strength [MPa]	9	11,5
Elongation at Break [%]	700	400
Tear [N/mm]	10	20

† The laboratory vulcanization conditions do not reflect the exposure to UV light during the processing; this time is only recommended for the static curing of slabs with UV light.

Typical data are average data and are not to be used as or to develop product specifications.

Regulatory Compliance

- The ingredients are listed in the BfR recommendation XV "Silicones". (1)
- These elastomers are compositionally compliant with 21 CFR 177.2600 - Rubber articles intended for repeated use and have been found, through testing of a representative sample, to meet the extractives limitations in 21 CFR 177.2600 (e and/or f). (2)
- A representative sample of an analogous grade to UV LSR 2030 und UV LSR 2060 has passed USP Class VI (United States Pharmacopeia 32, National Formulary 27, 2009. <88> Biological Reactivity Test, In Vivo tests) and ISO 10993 (Parts: 5, 6, 10, and 11) tests using Good Laboratory Practices (GLP). (3)

(1) Producer of the final article needs to test and confirm that the final product meets the analytical requirements and extraction/migration limits of BfR XV.

(2) It is the responsibility of the user to determine that the final product complies with the extractive limitations and other requirements of 21 CFR 177.2600 under their specific manufacturing procedures.

(3) Please contact the Momentive Performance Materials Product Regulatory Group for details.

Packaging

Silopren UV LSR 2030 and UV LSR 2060 liquid silicone rubbers are available as Drumkit (180 kg base and 3.6 kg catalyst) or Pailkit (15 kg base and 0.3 kg catalyst). Catalyst must not be exposed to light.

General Considerations for Use

Ready-to-use mixtures (of the components Base and Catalyst) are fed directly into the injection molding machine from the original containers by means of a metering and mixing unit. The container for the Catalyst-component must be protected from light. The mixture, consisting of the two components in the ratio 100:2, is injected into the mold. At room temperature the silicone rubber vulcanizes by exposure to UV light, without any dissociation products, within a short time.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement, or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment, if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular application(s).

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas

+1 800 295 2392

Toll free*

+704 805 6946

Direct Number

Latin America

Brazil

+55 11 4534 9650

Direct Number

Mexico

+52 55 2169 7670

Direct Number

EMEA- Europe, Middle East, Africa & India

Europe

+39 0510924300

Direct number

India, Middle East & Africa

+91 44 71212207

Direct number*

*All Middle Eastern countries, Africa, India, Pakistan, Bangladesh, Sri Lanka.

ASIA PACIFIC

China

800 820 0202

Toll free

+86 21 3860 4892

Direct number

Japan

+81 3 5544 3111

Direct number

Korea

+82 2 6201 4600

Direct number

South East Asia, Australia & New Zealand

+60 3 9206 1543

Direct number*

*South East Asia countries (Malaysia,

Singapore, Thailand, Indonesia,
Vietnam, Philippines, Cambodia,
Myanmar / other countries located in
Pacific region).

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS, AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER") ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS, OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service, or design in the infringement of any patent or other intellectual property right.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials, Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials, Inc.



260 Hudson River Road Waterford,
NY 12188 USA
momentive.com

Copyright 2023 Momentive Performance Materials, Inc. All rights reserved.